

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the application:

LISTING OF CLAIMS:

1. (currently amended): A pressure-sensitive adhesive tape comprising a supporting substrate ~~made of a plastic film~~ and a pressure-sensitive adhesive layer formed on at least one side of the supporting substrate, ~~an uneven portion of the supporting substrate~~ having an uneven portion on one side having a shape extending in the vertical direction against the longitudinal direction being disposed on one side of the supporting substrate, wherein a maximum stress at an elongation of not more than 50 % of the pressure-sensitive adhesive tape is larger than ~~at the~~ stress at break, wherein ~~an~~ the elongation at break of the pressure-sensitive adhesive tape is from 100 to 300 %, wherein the substrate is formed from a resin composition comprising ~~plastic film~~ ~~contains~~ high-density polyethylene and low-density polyethylene ~~where~~ having a density ~~of the low-density polyethylene is equal to or less than 0.919 g/cm³~~, wherein said high-density polyethylene and said low-density polyethylene are present in a weight percent ratio selected from the range of 10/90 to 90/10, and ~~wherein the plastic film contains a filler in an amount of not more than 5 parts by weight based on 100 parts by weight of the resin composition constituting the plastic film.~~

2. (currently amended): The pressure-sensitive adhesive tape according to claim 1, wherein the maximum stress at an elongation equal to or less than ~~of not more than~~ 50 % is at least 11 N/10 mm ~~or more~~.

3. (canceled).
4. (canceled).
5. (original): The pressure-sensitive adhesive tape according to claim 1, wherein the supporting substrate is transparent.
6. (previously presented): The pressure-sensitive adhesive tape according to claim 1, wherein the density of the low-density polyethylene is from 0.880 g/cm³ to 0.919 g/cm³.
7. (previously presented): The pressure-sensitive adhesive tape according to claim 1, wherein the density of the low-density polyethylene is from 0.910 g/cm³ to 0.919 g/cm³.
8. (currently amended): The pressure-sensitive adhesive tape according to claim 1, wherein ~~a~~ the density of the high-density polyethylene is from 0.940 g/cm³ to 0.970 g/cm³.
9. (currently amended): The pressure-sensitive adhesive tape according to claim 1, wherein ~~a~~ the density of the high-density polyethylene is from 0.950 g/cm³ to 0.965 g/cm³.